

TECHNICAL DATA SHEET

MAXITHEN[®] PP7A6657 Metallic Silver

Preparation of Pigments dispersed in Polypropylene for colouring of polyolefines

DOSAGE:	2% recommended value
HEAT STABILITY:	up to 300°C, determined on an injection moulding machine (residence time 5 minutes)
LIGHT FASTNESS:	7-8, determined according to DIN EN ISO 877. This assessment was undertaken in accordance with the blue wool scale (EN ISO 105-B01). Rating 8= best value, rating 1= worst value.
FORM OF SUPPLY:	Masterbatch in pellet form, packed in UV stabilised 20/25 kg PE bags, on pallets, covered with a UV stabilised hood (standard packaging). For colouring and stabilising the packaging material, a combined MAXITHEN [®] colour/UV/AO stabiliser masterbatch has been used to protect both, the packaging material as well as the content.
STORAGE CONDITIONS:	Storage time 36 months maximum. The product should be stored in a cool, dry location and be protected from sunlight and moisture. Once opened, bags should be kept tightly closed in order to prevent the absorption of moisture from the air.
ATTENTION:	This preparation contains shear sensitive effect pigments, there- fore all technical data's are only approximate figures. Therefore we recommend trials under practical conditions.

All information in this MAXITHEN[®] data sheet has been obtained from laboratory tests under ideal and closely controlled conditions. The information should act as a guide only and should not be construed as guaranteeing specific properties or suitability for a particular application. Therefore, trials by the customer using their polymer and their conditions are highly recommended.