

TECHNICAL DATA SHEET

MAXITHEN® UN1279 White

Singlepigmentpreparation dispersed in an universal thermoplastic carrier system

PIGMENTCONCENTRATION: 60 %

COLOUR INDEX: Pigment White 6

HEAT STABILITY: up to 300°C, determined on an injection moulding machine
(residence time 5 minutes)

LIGHT FASTNESS: 8, determined according to DIN EN ISO 877.
This assessment was undertaken in accordance with the blue wool scale
(EN ISO 105-B01). Rating 8= best value, rating 1= worst value.

FORM OF SUPPLY: Masterbatch in pellet form, packed in UV stabilised 20/25 kg PE bags, on
pallets, covered with a UV stabilised hood (standard packaging). For
colouring and stabilising the packaging material, a combined MAXITHEN®
colour/UV/AO stabiliser masterbatch has been used to protect both, the
packaging material as well as the content.

STORAGE CONDITIONS: Storage time 36 months maximum. The product should be stored in a cool,
dry location and be protected from sunlight and moisture. Once opened,
bags should be kept tightly closed in order to prevent the absorption of
moisture from the air.

All information in this MAXITHEN data sheet has been obtained from laboratory tests under ideal and closely controlled conditions. The information should act as a guide only and should not be construed as guaranteeing specific properties or suitability for a particular application. Therefore, trials by the customer using their polymer and their conditions are highly recommended.